

Durethan AKV 50 H1.0 000000

PA 66, injection molding grade, 50% glass fibers, good heat-ageing resistance

ISO Shortname: ISO 1874-PA 66,MHR,14-160,GF50

Property	Test Condition	Unit	Standard	Value	
				d.a.m.	cond.
Rheological properties					
C Melt volume-flow rate	290 °C; 5 kg	cm ³ /(10 min)	ISO 1133	19	
Molding shrinkage, parallel	150x105x3; 300 °C / MT 80 °C; 400 bar	%	acc. ISO 2577	0.23	
Molding shrinkage, transverse	150x105x3; 300 °C / MT 80 °C; 400 bar	%	acc. ISO 2577	1.25	
Post- shrinkage, parallel	150x105x3; 120 °C; 4 h	%	acc. ISO 2577	0.02	
Post- shrinkage, transverse	150x105x3; 120 °C; 4 h	%	acc. ISO 2577	0.03	
Mechanical properties (23 °C/50 % r. h.)					
C Tensile modulus	1 mm/min	MPa	ISO 527-1,-2	15700	10700
C Tensile Stress at break	5 mm/min	MPa	ISO 527-1,-2	220	170
C Tensile Strain at break	5 mm/min	%	ISO 527-1,-2	2.5	4.0
C Charpy impact strength	23 °C	kJ/m ²	ISO 179-1eU	95	95
C Charpy impact strength	-30 °C	kJ/m ²	ISO 179-1eU	100	100
C Charpy notched impact strength	23 °C	kJ/m ²	ISO 179-1eA	19	23
C Charpy notched impact strength	-30 °C	kJ/m ²	ISO 179-1eA	15	15
Izod notched impact strength	23 °C	kJ/m ²	ISO 180-1A	14	18
Izod notched impact strength	-30 °C	kJ/m ²	ISO 180-1A	11	11
Flexural modulus	2 mm/min	MPa	ISO 178	14000	10300
Flexural strength	2 mm/min	MPa	ISO 178	370	250
Flexural strain at flexural strength	2 mm/min	%	ISO 178	3.0	5.0
Flexural stress at 3.5 % strain	2 mm/min	MPa	ISO 178		235
Ball indentation hardness		N/mm ²	ISO 2039-1	290	160
Thermal properties					
C Melting temperature	10 °C/min	°C	ISO 11357-1,-3	263	
C Temperature of deflection under load	1.80 MPa	°C	ISO 75-1,-2	~250	
C Temperature of deflection under load	0.45 MPa	°C	ISO 75-1,-2	~250	
Vicat softening temperature	50 N; 120 °C/h	°C	ISO 306	> 230	
C Burning behavior UL 94 (1.6 mm)	1.6 mm	Class	UL 94	HB	
C Burning behavior UL 94	3.2 mm	Class	UL 94	HB	
C Oxygen index	Method A	%	ISO 4589-2	27	
Glow wire test (GWFI)	2.0 mm	°C	IEC 60695-2-12	600	
Electrical properties (23 °C/50 % r. h.)					
C Relative permittivity	100 Hz	-	IEC 60250	4.5	14
C Relative permittivity	1 MHz	-	IEC 60250	4.0	5.0
C Dissipation factor	100 Hz	10 ⁻⁴	IEC 60250	90	3200
C Dissipation factor	1 MHz	10 ⁻⁴	IEC 60250	150	850
C Volume resistivity		Ohm·m	IEC 60093	1E13	1E12



Durethan AKV 50 H1.0 000000

Property	Test Condition	Unit	Standard	Value	
				d.a.m.	cond.
C Surface resistivity		Ohm	IEC 60093	1E14	1E12
C Electric strength	1 mm	kV/mm	IEC 60243-1	40	35
C Comparative tracking index CTI	Solution A	Rating	IEC 60112	375	
Comparative tracking index CTI M	Solution B	Rating	IEC 60112	225 M	
Other properties (23 °C)					
C Water absorption (Saturation value)	Water at 23 °C	%	ISO 62	~4	
C Water absorption (Equilibrium value)	23 °C; 50 % RH	%	ISO 62	~1.4	
C Density		kg/m ³	ISO 1183	1570	
Glass fiber / glass bead / filler content		%	ISO 3451-1	50	
Bulk density		kg/m ³	ISO 60	~700	
Processing conditions for test specimens					
C Injection molding-Melt temperature		°C	ISO 294	300	
C Injection molding-Mold temperature		°C	ISO 294	80	
Processing recommendations					
Drying temperature		°C	-	80	
Drying time dry air dryer		h	-	2-6	
Residual moisture content		%	Acc. to Karl Fischer	0.03-0.12	
Melt temperature		°C	-	280-300	
Mold temperature		°C	-	80-120	

C These property characteristics are taken from the CAMPUS plastics data bank and are based on the international catalogue of basic data for plastics according to ISO 10350.



Durethan AKV 50 H1.0 000000

Disclaimer

Disclaimer for sales products

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Test values

Unless specified to the contrary, the values given have been established on standardized test specimens at room temperature. The figures should be regarded as guide values only and not as binding minimum values. Kindly note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mould/die, the processing conditions and the coloring.

Processing note

Under the recommended processing conditions small quantities of decomposition product may be given off during processing. To preclude any risk to the health and well-being of the machine operatives, tolerance limits for the work environment must be ensured by the provision of efficient exhaust ventilation and fresh air at the workplace in accordance with the Safety Data Sheet. In order to prevent the partial decomposition of the polymer and the generation of volatile decomposition products, the prescribed processing temperatures should not be substantially exceeded. Since excessively high temperatures are generally the result of operator error or defects in the heating system, special care and controls are essential in these areas.

Conditioning

Conditioning in accordance with ISO 1110 (70 °C; 62 % r.h.)

LANXESS DEUTSCHLAND GMBH | D - 51369 LEVERKUSEN

© LANXESS Deutschland GmbH

